

Information About Specialty Chemicals

To reorder call:
 Polysi Technologies
 (T) 1-866-4-POLYSI
 (4-765974)
 (F) 1-919-775-2460

DOW CORNING

DESCRIPTION

MOLYKOTE® 7409 Bonded Lubricant is a dispersion of solid lubricants in an organic resin-solvent system. When applied to metal surfaces it forms an extremely adherent, dry film with excellent corrosion-preventing properties and an operating temperature range of -70 to 380°C (-94 to 716°F). The solid lubricants provide a low coefficient of friction and high load-carrying capacity under conditions where conventional lubricants are ineffective or undesirable.

MOLYKOTE 7409 Bonded Lubricant is one of a range of bonded lubricants available from Dow Corning, each of which has been designed to meet particular handling, processing and operating conditions.

SPECIAL FEATURES

Special features of MOLYKOTE 7409 Bonded Lubricant include:

- High load-carrying capacity
- Long wear life
- Excellent corrosion-preventing properties
- Outstanding resistance to hydraulic fluids, oils and solvents
- Dry, nontacky film that does not attract dust
- Good adhesion, even when surface is not pretreated
- Use in very thin films (down to 3 microns)

USES

MOLYKOTE 7409 Bonded Lubricant is recommended to meet the following conditions:

- Very high loads, low speeds

MOLYKOTE® 7409 Bonded Lubricant

Type Dispersion of solid lubricants in an organic resin-solvent system
 Physical Form,
 as supplied Pourable liquid
 as cured Dry, lubricating film
 Color Dark gray
 Method of Application Spray, dip or brush
 Cure Heat cured
 Special Properties Exceptional resistance to aggressive hydraulic fluids and oils; excellent corrosion-preventing properties
 Primary Use Provides dry film lubrication and corrosion protection for metal parts

- Extreme temperatures
- When fretting is likely
- Corrosion of substrate must be prevented
- Dust is a problem
- Oil and grease are not acceptable
- Relubrication is not possible
- Very low friction is needed

Typical mechanisms or components on which MOLYKOTE 7409 Bonded Lubricant may be used are brake components; threaded fasteners; hydraulic parts as a replacement for

hard-chrome plating; miscellaneous components and mechanisms as a replacement for cadmium and zinc plating; hubs for aluminum wheels to prevent seizing; ball joints, piston skirts, etc.

HOW TO USE

MOLYKOTE 7409 Bonded Lubricant should be well mixed before use. Components to be coated should be cleaned and degreased thoroughly. To obtain optimum wear life and corrosion protection, use one of the surface pretreatments shown in Table I.

TABLE I: RECOMMENDED PRETREATMENTS FOR METAL SURFACES

Pretreatment	Stainless Steel		Plated Metals		Al	Cu	Mg	Ti
	Steel	Steel	Cr or Ni	Cd or Zn	Alloys	Alloys	Alloys	Alloys
Degrease	X	X	X	X	X	X	X	X
To remove oxides:								
Bright dip						X		
Sandblast	X	X	X					X
Anodize					X			
Dichromate							X	
Phosphate		X		X				
Oxalic acid	X							

TYPICAL PROPERTIES

These values are not intended for use in preparing specifications.

As Supplied

CTM 0020	Viscosity, DIN53211, 4-mm orifice, sec	85
	Specific Gravity	1.10
CTM 0090A	Flash Point, °C (°F)	28 (82)
	Cure Time,	
	at 150°C (302°F), hours	2
	at 220°C (428°F), hours	1
	Coverage, at 10 microns cured film thickness,	
	ft ² /lb	60

As Cured

	Recommended Dry Film Thickness, microns	5-15
	Coefficient of Friction (LFW-1),	
	after running-in	0.03
	Temperature Range, °C (°F)	-70 to 380 (-95 to 715)
	Load-Carrying Capacity (LFW-1),	
	N/cm ²	>80,000
CTM 0181	Adhesion	Good, even when applied to smooth surfaces
	Oil Resistance	Good after heat curing
	Resistance to Brake Fluid (DOT 3 and 4),	
	at 200°C (392°F)	Good after heat curing
CTM 0265	Corrosion Protection, salt spray test,	
	12 micron coating thickness applied over	
	zinc phosphate, hours	>300
	Wear Life (LFW-1), rotating, load 2860 N,	
	speed 72 rpm, 7.9 m/min, number of turns	
	until $\mu = 0.1$ (with phosphated substrate)	400,000

Specification Writers: Please obtain a copy of the Dow Corning Sales Specification for this product, and use it as a basis for your specifications. It may be obtained from any Dow Corning Sales Office, or from Dow Corning Customer Services in Midland, MI. Call (517) 496-6000.

The coating may be applied by spraying, dipping or brushing, but spraying usually produces the most uniform and precisely controlled film thickness. Dipping is also excellent for cylindrical parts or for irregularly shaped parts if a high degree of uniformity in film thickness is not essential.

Whichever method is used, regular or constant agitation is required to prevent settling of the solids.

Spraying

Use a commercial spray gun. A spray booth is desirable. Make sure the

working area is adequately ventilated and observe the usual precautions for spray painting. Spray from a distance of about 8 inches using a pressure of 4 to 5 atmospheres (60 to 75 psi). To obtain the best adhesion and wear life, apply a coating of 8 to 15 microns (0.3 to 0.6 mils).

A single wet pass of spray usually deposits a film of about this thickness. Useful performance can be obtained with coating down to 3 microns film thickness. Where uniformity is especially important, place the parts on a screen during spraying to minimize

excessive coating build-up due to “flashback.” Fitting the parts on a jig and rotating while spraying also helps.

Dipping

For cylindrical parts requiring a uniform, closely controlled film thickness, parts must be jigged vertically and withdrawn at a controlled rate determined by experiment to minimize “run-down.” When the coating thickness and uniformity are not critical, parts may be placed in a basket and dipped briefly.

Brushing

This method is recommended only where the other two methods are impractical. Use any ordinary paint brush.

CAUTION

MOLYKOTE 7409 Bonded Lubricant is a flammable product. The following precautions should be observed:

- The solvent may attack certain plastics
- Keep from heat and open flame
- Use only with adequate ventilation
- Avoid prolonged breathing of vapor
- Avoid prolonged or repeated skin contact
- Avoid eye contact

In case of eye contact, flush with plenty of water for 15 minutes. Obtain medical attention.

SHIPPING LIMITATIONS

D.O.T. Classification: flammable liquid.

STORAGE AND SHELF LIFE

Keep container closed. Shelf life for MOLYKOTE 7409 Bonded Lubricant is 60 months from date of manufacture.

PACKAGING

MOLYKOTE 7409 Bonded Lubricant is supplied in 11-lb (5-kg) containers, net weight.

SAFE HANDLING INFORMATION

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED. BEFORE HANDLING, READ PRODUCT AND MATERIAL SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE MATERIAL SAFETY DATA SHEET IS AVAILABLE FROM YOUR DOW CORNING REPRESENTATIVE, OR DISTRIBUTOR, OR BY WRITING TO DOW CORNING CUSTOMER SERVICES, OR BY CALLING (517) 496-6000.

LIMITED WARRANTY – PLEASE READ CAREFULLY

Dow Corning believes that the information in this publication is an accurate description of the typical characteristics and/or uses of the product or products, but it is your responsibility to thoroughly test the product in your specific application to determine its performance, efficacy and safety. Suggestions of uses should not be taken as inducements to infringe any particular patent.

Unless Dow Corning provides you with a specific written warranty of fitness for a particular use, Dow Corning’s sole warranty is that the product or products will meet Dow Corning’s then current sales specifications.

DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND OF FITNESS FOR USE. Your exclusive remedy and Dow Corning’s sole liability for breach of warranty is limited to refund of the purchase price or replacement of any product shown to be other than as warranted, and Dow Corning expressly disclaims any liability for incidental or consequential damages.

**DOW CORNING CORPORATION
MIDLAND, MICHIGAN 48686-0994**

"MOLYKOTE" is a registered trademark of Dow Corning Corporation.

Printed in U.S.A.

Form No. 71-499C-98

DOW CORNING

The logo consists of the words "DOW CORNING" in a bold, italicized, sans-serif font, centered within a solid black rectangular box. Below this box is a solid gray rectangular box.